


CHESHIRE MULTI BRICK



Manufacture - Manufactured in accordance with IS EN 771-1:2011

Accreditation - ISO 9001: 2015 and CE Certified

Dimensions - 215 x 102.5 x 65mm / 215 x 102.5 x 73mm

Weight - 2.10 Kg per brick

Density - 1970 Kg/m³

Tolerance/Range - T2/R1

Active Soluble Salts - S2

Frost Resistance - F2

Thermal Conductivity - 0.63 W/m.K

Reaction to Fire Class - A1

Bond Strength - 0.15 N/mm²

Average Weight of Pack - 975 Kg

Bricks per Pack – 556 / 512

Compressive Strength - ≥40 N/mm²

Water Absorption - ≤11%

SALES – GB

Mark Morris - Commercial Director

M: 07790 902 867

E: mark.morris@breedongroup.com

Colin Jones – Regional Sales Manager

M: 07436 284 072

E: colin.jones@breedongroup.com

Office – T: 028 92647100

E: productsales@breedongroup.com

SALES - IRELAND

Outhaus Group, Unit 26,
Airways Industrial Estate, Santry,
Dublin 17, D17 TH93.

T: +353 (0) 1 844 1205

E: info@kcmb.ie

www.kcmb.ie

MANUFACTURING

Drumgill,
Kingscourt,
Co. Cavan

T: (042) 966 7317

www.kingscourtbrick.com

DISCLAIMER:

The reproduction of colours and textures is only as accurate as the printing process will allow. Photographic samples should be used when shortlisting products but we advise that an actual sample should be seen before ordering.